

PlastiKote Trade Cold Zinc Primer

Ord.-no.: 440.0071025.076

Technical Information



High quality zinc spray to treat galvanised and untreated steel.

Quality & properties

- Fast drying
- Good filling property
- Outstanding cathodic corrosion prevention
- Resistant to petrol, chemicals and weather influences
- Spot-weldable
- Excellent adhesion

Physical & chemical data

- Vapour pressure: 4000/20 bar
- Content: 400 ml

How to use

- Before use, carefully read the directions on the packaging and act accordingly.
- The surface should be clean, dry and free of grease. Remove loose old lacquer and rust and sand the surface.
- The surface should be clean, dry and free of grease. The aerosol should have room temperature. Best processing temperature 10 to 25°C. Before use, shake the aerosol for 2 minutes and spray a sample. Distance to the surface to be treated approximately 25 to 30 centimeter.
- Apply the cold zinc primer in several thin layers. Before applying the next layer, again shake the aerosol. When desired, after drying a primer and a lacquer can be applied.
- After use, clean the valve (turn aerosol upside down and press the nozzle for approximately 5 seconds).

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as "special refuse".

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

For any further technical questions call our hotline +31 (0) 561 69 44 00 from Monday to Thursday from 9 h a.m. to 3 h p.m. or on Friday until 12 h p.m.

As of August 19, 2022 – This release replaces all eventually earlier issued versions.